

*Fusion*TM

SYNTHETIC **MACRO** FIBER BLEND


FABPROTM Polymers' **FUSIONTM**

Synthetic Macro Fiber Blend

FUSIONTM Synthetic Macro Blended Fibers are manufactured from a blend of 100% virgin polyolefin resins. FUSIONTM Fibers meet the requirements of ASTM C1116/C1116M "Standard Specification for Fiber-Reinforced Concrete", ASTM D7508/D7508M "Standard Specification for Polyolefin Chopped Strands for use in Concrete", and the requirements of ICC ES AC32 Section 3.1.1 for plastic shrinkage reinforcement and 3.1.2 for shrinkage and temperature reinforcement.

RECOMMENDED FOR USE IN:

- Industrial and warehouse floors
- Commercial slab construction
- Concrete pavement
- Whitetopping and overlays
- Thin wall precast
- Shotcrete
- Composite metal decks



FEATURES

FUSIONTM Synthetic Macro Fiber Blend is specifically engineered to replace steel fibers, welded-wire fabric (WWF), and conventional reinforcing bars when used as secondary reinforcement in slab-on-ground, thin wall and other precast applications.

FUSIONTM is a blend of FABPRO'S two "Best-In-Class", next-generation performance fibers — PERFORMAXTM and SPECTERTM — creating a synergy of reinforcement unequalled in our industry. FABPRO has captured plastic shrinkage and settlement reinforcement, secondary reinforcement, and post first-crack reinforcement – all in a single bag.

PERFORMAXTM is an excellent stand-alone macro fiber, possessing superior mechanical bonding properties, and compares favorably against other macro fibers when measured by ASTM C1399/C1399M. Merging with SPECTERTM ultra-thin cross section, and engineered to provide excellent plastic shrinkage crack reduction.

BENEFITS

- Eliminates the need for WWF and conventional steel bars as a secondary form of reinforcement. Does not replace primary/structural reinforcement.
- Delivers tight crack control.
- Provides excellent plastic shrinkage crack reduction and settlement control.
- Improves green strengths – permits earlier stripping of forms with less rejection.
- Reduces construction time and overall labor and material costs.
- Increases flexural toughness, impact and abrasion resistance.

PERFORMANCE CHARACTERISTICS

	PERFORMAX™	SPECTER™
Specific Gravity	0.91	0.91
Melting Point	320°F (160°C)	320°F (160°C)
Ignition Point	1,094°F (590°C)	1,094°F (590°C)
Absorption	Nil	Nil
Alkali Resistance	Excellent	Excellent
Tensile Strength	65,000 psi (448 MPa)	25,000 psi (170 MPa)
Fiber Length	1.5" (38 mm)	0.75" (19 mm)
Aspect Ratio	59	576
Chemical Resistance	Excellent	Excellent

GUIDELINES FOR USE

DOSAGE: The recommended dosage for FUSION™ Fibers is 4.5 lb/yd³ (2.7 kg/m³). This 4.5 lb/yd³ (2.7 kg/m³) dosage rate is approved for use in composite metal deck applications by the Steel Deck Institute under specification SDI C1.0 "Standard for Composite Steel Floor Deck". Different dosage rates may be appropriate depending on the application.

MIXING: FUSION™ Fibers are packaged in pre-weighed, ready-to-use, degradable bags which are designed to be introduced at any time before or during mixing of concrete produced in accordance with procedures specified in ASTM C94/C94M

ENGINEERING SPECIFICATIONS

FUSION™ Synthetic Macro Fiber Blend, when used at an appropriate dosage, is an option for the replacement of WWF and rebar as a safe and easy-to-use reinforcing system that is rust proof, alkali resistant, and compliant with industry codes when used in concrete mixed in accordance with ASTM C94/C94M. FUSION™ Fiber also meets ASTM C1399/C1399M ARS target values.

FUSION™ Synthetic Macro Fiber Blend should be specified for use in precast concrete, slabs-on-ground, and composite metal decks:

- To enhance post cure residual strength, toughness and durability
- To enhance post, first-crack performance
- To replace rebar and welded wire for secondary reinforcement
- To reduce handling and transportation stresses
- To reduce plastic shrinkage cracking
- To increase impact and abrasion resistance

FABPRO POLYMERS does not recommend this fiber for use in precast or slab-on-ground applications as a substitute for primary/structural reinforcement.

STORAGE AND HANDLING: FUSION™ Synthetic Macro Fiber Blend should be stored at temperatures below 140°F (60°C). Avoid storing near strong oxidizers and avoid sources of ignition. Use caution when stacking to avoid unstable conditions. Store in a sprinkled warehouse.

PACKAGING: FUSION™ Fibers are available in a variety of packaging options. Standard bag size is 4.5 lb (2.0 kg). Bags are packaged in ultradurable boxes with corner boards, palletized, and stretch-wrapped to prevent damage from shipping and handling.

SAFETY DATA SHEETS: FUSION™ Synthetic Macro Fiber Blend

For additional product information, contact your local sales representative or Customer Service at (800) 821-4391.



DISCLAIMER OF WARRANTIES & LIMITATION OF LIABILITY Seller and manufacturer do not make any warranty whatsoever regarding this product, either express or implied, including, without limitation, any implied warranty of merchantability, fitness for a particular purpose, condition, design or quality. Buyer's exclusive remedy and the seller's and the manufacturer's exclusive liability for any claims, losses, damages or injuries resulting from the use of this product, shall be limited to the replacement of the product with respect to which damages are claimed. In no case shall the seller or the manufacturer be liable for direct, consequential, special, incidental, punitive or indirect damages resulting from the purchase or use of this product. Buyer accepts this product subject to the foregoing disclaimer and purchases and uses this product at buyer's own risk. No employee or agent of seller or the manufacturer is authorized to vary the terms of this disclaimer in any manner. 12/21