



FABPRO™ Polymers' PERFORMAX™

Synthetic Macro Fiber

PERFORMAX™ Synthetic Macro
Fibers are manufactured from a blend
of 100% virgin polyolefin resins.
PERFORMAX™ Synthetic Macro
Fibers meet the requirements of ASTM
C1116/C1116M "Standard Specification
for Fiber-Reinforced Concrete" and the
requirements of ICC ES AC32 Section
3.1.1 for plastic shrinkage
reinforcement and 3.1.2 for shrinkage
and temperature reinforcement.

RECOMMENDED FOR USE IN:

- · Industrial and warehouse floors
- Commercial slab construction
- Concrete pavement
- Whitetopping and overlays
- Thin wall precast
- Shotcrete
- Composite metal decks
- · Marine elements
- Vaults, septic tanks & containers



FEATURES

PERFORMAXTM Synthetic Macro Fibers are uniquely engineered to provide "Built-In Reinforcement" as a replacement for steel fibers, welded-wire fabric (WWF) and conventional reinforcing bars in a variety of secondary reinforcement applications. In addition, PERFORMAXTM Synthetic Macro Fibers help to minimize temperature shrinkage cracking, plastic settlement and plastic shrinkage cracking. Other features include:

- · Improved worksite safety by eliminating handling of WWF and light rebar
- · Uniform distribution of fibers throughout the concrete matrix
- Excellent finish-ability
- · Superb post-first crack performance

BENEFITS

- Eliminates the need for WWF and conventional steel bars as a secondary form of reinforcement. Does not replace primary/structural reinforcement.
- · Delivers tight crack control.
- · Provides excellent plastic shrinkage crack reduction and settlement control.
- Improves green strengths permits earlier stripping of forms with less rejection.
- · Reduces construction time and overall labor and material costs.
- · Increases flexural toughness, impact and abrasion resistance.



PERFORMANCE CHARACTERISTICS

Specific Gravity	0.91
Melting Point	320°F (160°C)
Ignition Point	1,094°F (590°C)
Absorption	Nil
Alkali Resistance	Excellent
Tensile Strength	65,000 psi (448 MPa)
Length	1.5'' (38 mm)
Aspect Ratio	59 for 1.5" cut length
Chemical Resistance	Excellent

GUIDELINES FOR USE

DOSAGE: The recommended dosage for the PERFORMAX[™] Synthetic Macro Fibers is 3 lb/yd³ (1.8 kg/m³). It can be used at dosage rates from 3 lb/yd³ (1.8 kg/m³) up to 13 lb/yd³ (7.8 kg/m³) or the equivalent dosage of 0.2% to 0.9% by volume, unless otherwise specified. For composite metal deck applications, minimum dosage is 4 lb/yd3 (2.4 kg/m³) as recommended by the Steel Deck Institute (SDI C-1.0) design code provisions.

MIXING: PERFORMAX[™] Synthetic Macro Fibers are packaged in pre-weighed, ready-to-use, degradable bags which are designed to be introduced at any time before or during mixing of concrete produced in accordance with procedures specified in ASTM C94/C94M.

ENGINEERING SPECIFICATIONS

PERFORMAX™ Synthetic Macro Fiber, when used at an appropriate dosage, is an option for the replacement of WWF and rebar as a safe and easy-to-use reinforcing system. The fiber is rust proof, alkali resistant, and compliant with industry codes when used in concrete mixed in accordance with ASTM C94/C94M.

PERFORMAX™ Synthetic Macro Fiber should be specified for use in concrete slabs:

- · To enhance residual strength, toughness and durability
- To reduce plastic shrinkage cracking
- · To increase abrasion resistance
- · To improve impact resistance
- To reduce permeability

FABPRO POLYMERS does not recommend this fiber for use in slabs as a substitute for primary/structural reinforcement.

STORAGE AND HANDLING: PERFORMAX™ Synthetic Macro Fibers should be stored at temperatures below 140°F (60°C). Avoid storing near strong oxidizers and avoid sources of ignition. Use caution when stacking to avoid unstable conditions. Store in a sprinkled warehouse.

PACKAGING: PERFORMAX™ Synthetic Macro Fibers are packaged in preweighed degradable 3 lb (1.36 kg), 4 lb (1.81 kg) and 5 lb (2.27 kg) bags that can be added directly to the mixing system.

SAFETY DATA SHEETS: PERFORMAX™ Synthetic Macro Fiber

USA

For additional product information, contact your local sales representative or Customer Service at (800) 821-4391.