

PERFORMAXTM
SYNTHETIC MACRO FIBER **HT**

FABPROTM Polymers'
PERFORMAXTM HT

Synthetic Macro Fiber

PERFORMAXTM HT Synthetic High Tensile Macro Fibers are manufactured from a blend of 100% virgin polyolefin resins. PERFORMAXTM HT Synthetic Macro Fibers meet the requirements of ASTM C1116/C1116M "Standard Specification for Fiber-Reinforced Concrete" and the requirements of ICC ES AC32 Section 3.1.1 for plastic shrinkage reinforcement and 3.1.2 for shrinkage and temperature reinforcement.

RECOMMENDED FOR USE IN:

- Industrial and warehouse floors
- Commercial slab construction
- Concrete pavement
- Whitetopping and overlays
- Thin wall precast
- Shotcrete
- Composite metal decks
- Marine elements
- Vaults, septic tanks & containers



FEATURES

PERFORMAXTM HT Synthetic High Tensile Macro Fibers are uniquely engineered with higher tensile strength to provide better "Built-In Reinforcement" as a replacement for steel fibers, welded-wire fabric (WWF) and conventional reinforcing bars in a variety of secondary reinforcement applications. In addition, PERFORMAXTM HT Synthetic High Tensile Macro Fibers help to minimize temperature shrinkage cracking, plastic settlement and plastic shrinkage cracking. Other features include:

- Improved worksite safety by eliminating handling of WWF and light rebar
- Uniform distribution of fibers throughout the concrete matrix
- Excellent finish-ability
- Superb post-first crack performance

BENEFITS

- Eliminates the need for WWF and conventional steel bars as a secondary form of reinforcement. Does not replace primary/structural reinforcement.
- Delivers tight crack control.
- Provides excellent plastic shrinkage crack reduction and settlement control.
- Improves green strengths – permits earlier stripping of forms with less rejection.
- Reduces construction time and overall labor and material costs.
- Increases flexural toughness, impact and abrasion resistance.

PERFORMANCE CHARACTERISTICS

Specific Gravity	0.91
Melting Point	320°F (160°C)
Ignition Point	1,094°F (590°C)
Absorption	Nil
Alkali Resistance	Excellent
Tensile Strength	75,000 psi (515 MPa)
Length	1.5" (38 mm)
Chemical Resistance	Excellent

GUIDELINES FOR USE

DOSAGE: The recommended dosage for the PERFORMAX™ HT Synthetic Macro Fibers is 3 lb/yd³ (1.8 kg/m³). It can be used at dosage rates from 3 lb/yd³ (1.8 kg/m³) up to 13 lb/yd³ (7.8 kg/m³) or the equivalent dosage of 0.2% to 0.9% by volume, unless otherwise specified.

For composite metal deck applications, minimum dosage is 4 lb/yd³ (2.4 kg/m³) as recommended by the Steel Deck Institute (SDI C-1.0) design code provisions.

MIXING: PERFORMAX™ HT Synthetic Macro Fibers are packaged in pre-weighed, ready-to-use, degradable bags which are designed to be introduced at any time before or during mixing of concrete produced in accordance with procedures specified in ASTM C94/C94M.

ENGINEERING SPECIFICATIONS

PERFORMAX™ HT Synthetic Macro Fiber, when used at an appropriate dosage, is an option for the replacement of WWF and rebar as a safe and easy-to-use reinforcing system. The fiber is rust proof, alkali resistant, and compliant with industry codes when used in concrete mixed in accordance with ASTM C94/C94M.

PERFORMAX™ HT Synthetic Macro Fiber should be specified for use in concrete slabs:

- To enhance residual strength, toughness and durability
- To reduce plastic shrinkage cracking
- To increase abrasion resistance
- To improve impact resistance
- To reduce permeability

FABPRO POLYMERS does not recommend this fiber for use in slabs as a substitute for primary/structural reinforcement.

STORAGE AND HANDLING: PERFORMAX™ HT Synthetic Macro Fibers should be stored at temperatures below 140°F (60°C). Avoid storing near strong oxidizers and avoid sources of ignition. Use caution when stacking to avoid unstable conditions. Store in a sprinkled warehouse.

PACKAGING: PERFORMAX™ HT Synthetic Macro Fibers are packaged in preweighed degradable 3 lb (1.36 kg), 4 lb (1.81 kg) and 5 lb (2.27 kg) bags that can be added directly to the mixing system.

SAFETY DATA SHEETS: PERFORMAX™ HT Synthetic Macro Fiber

For additional product information, contact your local sales representative or Customer Service at (800) 821-4391.



DISCLAIMER OF WARRANTIES & LIMITATION OF LIABILITY Seller and manufacturer do not make any warranty whatsoever regarding this product, either express or implied, including, without limitation, any implied warranty of merchantability, fitness for a particular purpose, condition, design or quality. Buyer's exclusive remedy and the seller's and the manufacturer's exclusive liability for any claims, losses, damages or injuries resulting from the use of this product, shall be limited to the replacement of the product with respect to which damages are claimed. In no case shall the seller or the manufacturer be liable for direct, consequential, special, incidental, punitive or indirect damages resulting from the purchase or use of this product. Buyer accepts this product subject to the foregoing disclaimer and purchases and uses this product at buyer's own risk. No employee or agent of seller or the manufacturer is authorized to vary the terms of this disclaimer in any manner. 12/21